

Claim Amendments

1. (previously presented) A biodegradable recycled polyester resin, which is obtained by a process including the step of carrying out a reaction of a recycled aromatic polyester (A) with an aliphatic polyester (B) having a number-average molecular weight of 3,000 to 300,000 in a reaction ratio (weight ratio) of (A)/(B) = 95/5 to 5/95, thereby affording biodegradability to the recycled aromatic polyester (A), wherein the aliphatic polyester (B) is obtained from an aliphatic dicarboxylic acid component having 2 to 6 carbon atoms and an aliphatic glycol component having 2 to 4 carbon atoms.

2. (canceled).

3. (original) A biodegradable recycled polyester resin according to claim 1, wherein the aliphatic polyester (B) is obtained by a process including the step of carrying out ring-opening copolymerization of a cyclic acid anhydride (C) and a cyclic ether (D), wherein the cyclic acid anhydride (C) includes succinic anhydride as a major component, and wherein the cyclic ether (D) includes ethylene oxide as a major component.

4. (canceled).

5. (original) A biodegradable recycled polyester resin according to claim 1, which has a structure such that the recycled aromatic polyester (A) and the aliphatic polyester (B) are arranged in a block form.

6. (canceled).

7. (original) A biodegradable recycled polyester resin according to claim 3, which has a structure such that the

(15963.DOC)

(Amendment and Remarks--page 2 of 7)

recycled aromatic polyester (A) and the aliphatic polyester (B) are arranged in a block form.

8. (canceled).

9. (previously presented) A production process for a biodegradable recycled polyester resin, which comprises the step of carrying out a melting reaction of a recycled aromatic polyester (A) with an aliphatic polyester (B) in a heated state in a reaction ratio (weight ratio) of (A)/(B) = 95/5 to 5/95, wherein the aliphatic polyester (B) has a number-average molecular weight of 3,000 to 300,000, and wherein the aliphatic polyester (B) is obtained from an aliphatic dicarboxylic acid component having 2 to 6 carbon atoms and an aliphatic glycol component having 2 to 4 carbon atoms.

{15963.DOC}

(Amendment and Remarks—page 3 of 7)